ATLAS OF ZEOLITE STRUCTURE TYPES

W.M. Meier, D.H. Olson and Ch. Baerlocher

Fourth Revised Edition
1996

Published on behalf of the
Structure Commission of the International Zeolite Association

by

Elsevier
London Boston Singapore Sydney Toronto Wellington

First edition 1978, published by the Structure Commission of the International Zeolite Association

Second revised edition, 1987

Third revised edition, 1992

Library of Congress Cataloging-in-Publication Data
Meier, Walter.
Atlas of zeolite structure types.—4th rev. ed./W.M. Meier, D.H. Olson, and Ch. Baerlocher.
p. cm.
Includes Index.
1. Zeolites I. Olson, David. II. Baerlocher, Ch.
III. International Zeolite Association. Structure Commission. IV. Title
TP248.S5M45 1996 660'.284--dc20 96-19173

ISBN 0-444-10015-6 (pbk. : alk. paper)

ERI ERIONITE $P6_3/mmc$

Framework density: 15.6 T/1000 Å^3

Loop configuration of T-atoms:



Coordination sequences:
T_1(24) 4 9 17 30 50 75 98 118 144 185
T_2(12) 4 10 20 32 46 64 90 126 164 196

Channels: ⊥ [001] **8** 3.6 x 5.1***

Type material: **Erionite** $(Na_2,Ca..)_{3.5}K_2[Al_9Si_{27}O_{72}] \cdot 27\ H_2O$
hexagonal, $P6_3/mmc$, a=13.3, c=15.1 Å[1-3]

Framework description: AABAAC sequence of 6-rings

Isotypic framework structures: $AlPO_4$-17 plus numerous compositional variants[4,5]
LZ-220[6]
Linde T (ERI-OFF structural intermediate)[7]

References:

(1) L. W. Staples and J. A. Gard, Mineral. Mag. 32, 261 (1959).
(2) A. Kawahara and H. Curien, Bull. Soc. Fr. Mineral. Crystallogr. 92, 250 (1969).
(3) J. A. Gard and J. M. Tait, Proc. 3rd IZC, Recent Progress Reports (Leuven UP, 1973), p 94.
(4) J. J. Pluth, J. V. Smith and J. M. Bennett, Acta Cryst. C42, 283 (1986).
(5) See AEL ref. 2.
(6) D. W. Breck and G. W. Skeels, US Patent 4,503,023 (1985).
(7) D. W. Breck, Zeolite Molecular Sieves (Wiley, 1974), p 173.

FAU FAUJASITE $Fd\bar{3}m$

Framework density: 12.7 T/1000 Å^3

Loop configuration of T-atoms:



Coordination sequences: T(192) 4 9 16 25 37 53 73 96 120 145

Channels: <111> **12** 7.4***

Type material: **Faujasite** $(Na_2,Ca,Mg)_{29}[Al_{58}Si_{134}O_{384}] \cdot 240\ H_2O$
cubic, $Fd\bar{3}m$, a=24.7 Å[1,2]

Isotypic framework structures:
Beryllophosphate X[3]
CSZ-1 (EMT-FAU structural intermediate)[4]
ECR-30 (EMT-FAU structural intermediate)[5]
Linde X[6,7]
Linde Y[8,9]
LZ-210[10]
SAPO-37[11]
Zincophosphate X[3]
ZSM-20 (EMT-FAU structural intermediate)[12]
ZSM-3 (EMT-FAU structural intermediate)[13]
and numerous other compositional variants

References:

(1) G. Bergerhoff, W. H. Baur and W. Nowacki, N. Jb. Miner. Mh. **1958**, 193 (1958)
(2) W. H. Baur, Am. Mineral. **49**, 697 (1964)
(3) T. E. Gier and G. D. Stucky, Zeolites **12**, 770 (1992).
(4) M. G. Barrett and D. E. W. Vaughan, UK Patent GB 2,076, 793 A (1981).

LTL — LINDE TYPE L — P6/mmm

Framework density: 16.4 T/1000 Å^3

Loop configuration of T-atoms:



Coordination sequences:

T_1(24) 4 9 17 29 46 69 98 131 162 187

T_2(12) 4 10 21 35 49 66 89 117 150 190

Channels: [001] **12** 7.1*

Type material: **Linde Type L** $K_6Na_3[Al_9Si_{27}O_{72}] \cdot 21\ H_2O$
hexagonal, P6/mmm, a=18.4, c=7.5 Å[1]

Isotypic framework structures:
Gallosilicate L[2,3]
(K,Ba)-G,L[4]
LZ-212[5]
Perlialite[6,7]

References:

(1) R. M. Barrer and H. Villiger, Z. Kristallogr. **128**, 352 (1969).
(2) P. A. Wright, J. M. Thomas, A. K. Cheetham, A. K. Nowak, Nature **318**, 611 (1985).
(3) J. M. Newsam, Mater. Res. Bull. **21**, 661 (1986).
(4) C. Baerlocher and R.M. Barrer, Z. Kristallogr. **136**, 245 (1972).
(5) D. W. Breck and G. W. Skeels, US Patent 4,503,023 (1985).
(6) G. Artioli and A. Kvick, Eur. J. Mineral. **2**, 749 (1990).
(7) Y. P. Menshikov, Zap. Vses. Mineral. O-va. **113**, 607 (1984).

MOR MORDENITE Cmcm

Framework density: 17.2 T/1000 Å^3

Loop configuration of T-atoms:



Coordination sequences:

T_1(16) 4 12 22 38 60 88 115 155 204 242
T_2(16) 4 12 20 37 64 87 114 154 198 241
T_3 (8) 4 11 24 39 54 86 126 156 195 242
T_4 (8) 4 11 24 39 60 92 122 148 195 250

Channels: [001] **12** 6.5 x 7.0* ↔ [010] **8** 2.6 x 5.7*

Type material: **Mordenite** $Na_8[Al_8Si_{40}O_{96}] \cdot 24\ H_2O$
orthorhombic, Cmcm, a=18.1, b=20.5, c=7.5 Å[1]

Isotypic framework structures:

Ca-Q[2]
Gallosilicate MOR[3]
Large port mordenite[4]
LZ-211[5]
Maricopaite (interrupted framework)[6]
Na-D[7]
Zeolon

Alternate designations:

Ptilolite
Arduinite (discredited)
Flokite (discredited)

References:

(1) W. M. Meier, Z. Kristallogr. **115**, 439 (1961).
(2) M. Koizumi and R. Roy, J. Geol. **68**, 41 (1960).
(3) M.J. Eapen, K.S.N. Reddy, P.N. Joshi and V.P. Shiralkar, J. Incl. Phen. Mol. Recogn. Chem. **14**, 119 (1992).
(4) L. B. Sand, Molecular Sieves, Soc. of Chem. Industry, London, p. 71 (1968).
(5) D. W. Breck and G. W. Skeels, US Patent 4,503,023 (1985).
(6) R. Rouse and D. R. Peacor, Am. Mineral. **79**, 175 (1994).
(7) R. M. Barrer and E. A. D. White, J. Chem. Soc. **1952**, 1561 (1952).

OFF — OFFRETITE — $P\bar{6}m2$

Framework density: 15.5 T/1000 Å^3

Loop configuration of T-atoms:



Coordination sequences:

T_1(12) 4 9 17 30 50 75 98 118 144 185
T_2(6) 4 10 20 32 46 66 94 128 162 192

Channels: [001] **12** 6.7* ↔ ⊥ [001] **8** 3.6 x 4.9**

Type material: **Offretite** $(Ca,Mg)_{1.5}K[Al_4Si_{14}O_{36}] \cdot 14\,H_2O$
hexagonal, $P\bar{6}m2$, a=13.3, c=7.6 Å[1,2]

Framework description: AAB sequence of 6-rings

Isotypic framework structures: Linde T (ERI-OFF structural intermediate)[3]
LZ-217[4]
TMA-O[5]

References:

(1) J. M. Bennett and J. A. Gard, Nature **214**, 1005 (1967).
(2) J. A. Gard and J. M. Tait, Acta Cryst. **B28**, 825 (1972).
(3) D. W. Breck, Zeolite Molecular Sieves (Wiley, 1974) p. 103.
(4) D. W. Breck and G. W. Skeels, US Patent 4,503,023 (1985).
(5) R. Aiello, R. M. Barrer, J. A. Davies and I. S. Kerr, Trans. Farad. Soc. **66**, 1610 (1970).